

STOPAQ® WRAPPINGBAND CZ

Product Information

Product description: Stopaq® Wrappingband CZ is a low temperature corrosion preventing wrap material adhering extremely well to steel and factory applied pipeline coatings like PE, Liquid Epoxies and FBE. Due to its high tack it is very suitable for application under cold ambient and substrate temperatures.

Stopaq® Wrappingband CZ is a non-toxic, cold-applied, prefabricated wrap coating, based on a compound consisting of non-crystalline, low-viscosity, non-crosslinked (fully amorphous), pure homopolymer Polyisobutene. It is viscous at the indicated operating temperatures and due to its liquid nature, it has a set of unique properties like cold-flow into all irregularities of the substrate and self-healing of the complete coating system. The compound does not cure and is unable to build up internal stress. It is fully resistant to water and has a low gas- and water vapour permeability.

Stopaq® Wrappingband CZ requires application of a polymeric outer wrap like Stopaq® Outerwrap (various types available) or Stopaq® High Impact Shield. This improves impact and indentation resistance of the coating system and supports the self-healing ability of small damages like dents and cuts. Optionally, additional mechanical protective layers can be applied on top like Stopaq® Polyester or Stopaq® Outerglass Shield

Features:

- Controlled cold flow providing permanent inflow into the finest pores of the substrate
- Resistant to low temperatures without getting brittle
- Conforms to irregular shapes
- Low surface tension; adheres on many types of dry substrates at a molecular level
- Surface tolerant: no blasting techniques required, wire brushing is sufficient (ISO 8501-1: St 2)
- Constant film thickness
- Adhesion based on vanderWaals forces
- Self-healing of small dents, voids and cracks
- Inert to ageing and weathering
- Resistant to many chemicals like water, salts, acids, alkalis, polar solvents, etc. For additional information, please contact Stopaq B.V.

Benefits:

- Safe to use. No physical, health or environmental hazards.
- Fast and easy field application
- Can be moulded onto various types of irregular shaped objects
- No osmosis or under film migration of moisture
- No cathodic disbondment
- Cathodic Protection (CP) of steel structures is not affected

Product certificates:

- KIWA: "Kiwa Product certificate for corrosion protection compound and tapes for tank and pipeline installations according to the Evaluation Guideline BRL-K911/02 with a verification according to standard EN-12068."
- DVGW: DIN 30672

Application examples

Pipes and vessels: For protection against external corrosion of buried or submerged carbon steel, alloy steel and ductile iron pipelines and vessels.

Field joints: For protection against external corrosion of buried or submerged carbon steel and alloy steel pipeline girth-weld joints.

Fittings: For protection against external corrosion of buried or submerged carbon steel, alloy steel and ductile iron pipe fittings such as elbows, bends, tees, reducers, flanges, etc.

Pipe coating repair and rehabilitation: For coating repair and rehabilitation of pipeline coating defects as e.g. in accordance with ISO 21809-11.

Product properties of Stopaq® Wrappingband CZ

Colour	Green
Thickness	2,0 ± 0,2 mm [80 ± 8 mils] ^{A)}
Density	1,5 ± 0,1 g/cm ³ [12.5 ± 0.8 lbs/gal] (ISO 1183-1)
Mass / area	3,0 ± 0,3 kg/m ² [0.614 lbs/sq.ft]
Temperature ranges	Thermal resistance: +70 °C [158 °F] Continuous buried and submerged services: -45 to +50 °C [-49 to 122 °F]
Glass transition temp.	≤ -65 °C [-85 °F] ^{A), B)}
Crystallization temp.	Tested range -100 °C to +190 °C [-148 °F to +374 °F] ^{A)} : - No evidence of crystallization or melting point.
Holiday detection	No holidays at 15 kV ^{A)}
Drip resistance	Tested 48 h at +130 °C [+266 °F] ^{A), B)} : - No dripping of compound
Specific electrical insulation resistance	R _{S100} ≥ 10 ⁸ (1E+08) Ω.m ² [≥ 10 ⁹ (1E+09) Ω.ft ²] ^{A), B)}
Adhesion	Peel tests on carbon steel (Sa 2½, St 3, and St 2) and plant coating PE ^{A)} Peel strengths before ageing: ^{A)} - at +23 °C [+73 °F] ≥ 0,04 N/mm [≥ 3.6 ozf/in] - at +50 °C [+122 °F] ≥ 0,02 N/mm [≥ 1.8 ozf/in] Peel strengths after hot water immersion and after thermal ageing, both for 100 days at 70 °C [+158 °F]: ^{A)} - at +23 °C [+73 °F] ≥ 0,04 N/mm [≥ 3.6 ozf/in] - at +50 °C [+122 °F] ≥ 0,02 N/mm [≥ 1.8 ozf/in] In all cases cohesive separation mode and ≥ 95% coverage of surface
Lap shear resistance	Tested on carbon steel Sa 2½ ^{A), B)} - Lap shear strengths: - at +23 °C [+73 °F] ≥ 0,004 N/mm ² [≥ 0.58 psi] - at +50 °C [+122 °F] ≥ 0,002 N/mm ² [≥ 0.29 psi] In all cases cohesive separation mode and ≥ 95% coverage of surface
Properties of complete coating system	
Construction	- 1 layer of Stopaq® Wrappingband CZ - 2 layers of Stopaq® Outerwrap
Thickness	3,0 ± 0,3 mm [120 ± 12 mils]
Impact resistance	Tested with 15 J [132 in.lbf] at +23 °C [+73 °F] ^{A), B)} : - No holidays
Indentation resistance	Tested with 1,0 N/mm ² [145 psi] at +23 and +50 °C [+73 and +122 °F] ^{A), B)} : - Residual thickness ≥ 0,6 mm [24 mils]
Cathodic disbondment resistance	Tested at +23 and +50 °C [+73 and +122 °F] ^{A), B)} : - Disbondment 0 mm, no holiday. Defect Ø 6 mm [1/4"] self-healed within 1 day.
Self-healing test	Artificial defect Ø 6mm [1/4"] tested for completion of self-healing: - at +23 °C [+73 °F]: completed < 24 hours, no holiday - at +50 °C [+122 °F]: completed < 24 hours, no holiday

^{A)} ISO 21809-3:2016 coating type 13; ^{B)} KIWA BRL-K911/02

General order information

Product	Stopaq® Wrappingband CZ is available in rolls of various widths and lengths (other sizes on request):
Art. Nr.:	Product dimensions and contents:
4250	50mm x 5m [2"x16.5']; 24 pcs/box; 576 pcs/pallet
4235	50mm x 10m [2"x33']; 12 pcs/box; 360 pcs/pallet
4240	100mm x 10m [4"x33']; 6 pcs/box; 180 pcs/pallet
6127	200mm x 10m [8"x33']; 2 pcs/box; 96 pcs/pallet
4247	300mm x 10m [12"x33']; 2 pcs/box; 80 pcs/pallet
Handling	Handle with care. Keep boxes upright.
Storage	Store indoor, clean and dry, away from direct sunlight in a cool place below +35 °C [95 °F]. Unlimited shelf life.

Application instruction - Job preparation	
Tools, equipment and auxiliaries	<ul style="list-style-type: none"> – Temperature probe, Dew point tester, High voltage holiday tester – Scissors, Knife, Measuring tape – Abrasive cleaning pads, Wire brushes – SFL™ Cleaning Wipes or Isopropyl alcohol, cas. nr. 67-63-0 – Personal protective gear
Additional coating materials	Stopaq® Wrappingband CZ requires application of a polymeric outer wrap, such as: <ul style="list-style-type: none"> – Stopaq® Outerwrap Flex PE / PE / PVC / HSPE / HSPEX – Stopaq® High Impact Shield Optionally, additional mechanical protective layers can be applied over the complete coating, like: <ul style="list-style-type: none"> – Stopaq® Outerglass Shield – Stopaq® Polyester
Work area and substrate	The substrate must be dry, clean and protected against negative weather influences.
Product conditions	Stopaq® Wrappingband CZ must be dry and the temperature should preferably be above 0 °C [+32 °F] for the ease of application.

Application instruction - Surface preparation	
General	The area to be coated must be clean, dry, and free from oil, grease and dust. All contamination including mill-scale must be removed.
Degreasing	Degrease surfaces with SFL™ Cleaning Wipes or Isopropyl alcohol and e.g. a lint-free cloth.
Substrate temperature	Prior to and during the application, the temperature of the substrate(s) must be at least 3 °C [6 °F] above the dew point. Temperature of the substrate should preferably be above 0 °C [+32 °F] for fast and easy application. Preheating may be required.
Carbon Steel	Minimum requirement for surface preparation is St 2 according to ISO 8501-1. Roughness profile is not essential for adhesion.
Existing coating - Bitumen	Remove loose bitumen. For proper adhesion, make sure that the surface is clean and dry. The product must not be applied on moist bitumen. Moderate heating of bitumen is recommended in order to let trapped water evaporate. After this, bitumen should be allowed to cool down to preferred substrate temperature.
Other substrates	De-gloss and degrease the surfaces with SFL™ Cleaning Wipes or with isopropyl alcohol and an abrasive pad.
Cleanliness check	Take a piece of Stopaq® Wrappingband CZ of ± 150 mm [6"] length, remove the release liner and fold it back for about 25 mm [1"]. Apply it to the surface, press it firmly and leave it for 5 minutes. Pull the Wrappingband from the substrate with an angle of approx. 135 deg. and a speed of 100 mm/min [4"/min]. Cohesive separation should occur and coverage of the surface with remaining material should be ≥ 95%. If this is less, surface cleaning is insufficient. At too low substrate temperatures this test may not be successful. Preheat the substrate to preferred temperature and repeat the test.

Application instruction – Brief version	
See specific Stopaq coating instructions for e.g. field joints, pipe wrapping, coating repair, fittings, etc.	
Wrapping	Start with removal of a small part of the release liner and apply Stopaq® Wrappingband CZ on the substrate. Apply without tension and avoid air entrapment. Mould the Wrappingband tight onto the substrate.
Release liner	Do not remove the release liner from Stopaq® Wrappingband CZ until just before application to the substrate.
Overlap of wraps	Side-by-side overlap: ≥ 10 mm [3/8"] Consecutive rolls: ≥ 50 mm [2"] Overlap on existing coatings: See specific Stopaq application instructions.
Visual inspection	The appearance of Stopaq® Wrappingband CZ should look smooth and tight, and should be shaped around all details and into corners.
Holiday detection	The coated surface must be checked for holidays with a high voltage holiday detector at 15 kV equipped with a brush probe prior to application of any outer wrap material.
Application of outer wrap materials	Stopaq® Wrappingband CZ must be protected against impacts, indentations, soil pressure and other influences by application of Stopaq® Outerwrap or Stopaq® High Impact Shield. Optionally, additional mechanical protective materials like Stopaq® Outerglass Shield or Stopaq® Polyester can be installed over the complete coating system. Please contact Stopaq B.V. for further information.

Handling and commissioning	
Exposure to loads	Objects coated with Stopaq® Wrappingband CZ should not be exposed to loads e.g. from supports- or lifting equipment.
Immersion or burying	Immersion or burying is possible immediately after completion of the coating application. See data sheets for specific instructions of additional materials used. Backfill and compact with clean sand and filling material without sharp stones or hard lumps of soil.

Information	
Documentation	Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.



Seal For Life Industries - Stopaq B.V.
Stadskanaal, the Netherlands
Tel: +31 599 696 170

Seal For Life Industries BV
Westerlo, Belgium
Tel: +32 14 722 500

Seal For Life Industries US LLC
San Diego, USA
Tel: +1 858 633 9785

Seal For Life Industries Mexico
S de R.L. de C.V.
Tijuana, Mexico
US Tel: +1 858 633 9785
MX Tel: +52 664 647 4300

Seal For Life India Private Ltd.
Baroda, India
Tel: +91 2667 264 721

Further information is available on our website www.sealforlife.com, or by sending an inquiry to info@sealforlife.com

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal for Life's liability is stated in its General Terms and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.