

# **SFL ROCKSHIELD 11 MM**

## **Product Information**

**Product description:** SFL Rockshield 11 mm is a pipeline protection mesh for protecting pipeline coatings from rock backfills. It cushions the impact of rocks or hard backfill which can cause damage to installed coating systems. It also offers protection from abrasive objects after installation of coated systems, prohibiting geologic movements from damaging pipelines. It can also be used for offshore purposes to protect against impact damage by lay barge rollers, anchors, rock placement, infill and fishing (trawl) activities.

SFL Rockshield 11 mm is a diamond structured mesh manufactured from high density polyethylene to produce a strong cushioning structure.

#### **Features**

- Flexible for easy handling at low temperatures
- Chemically inert, will not rot
- High impact strength and tensile strength
- Manufactured to withstand extreme weather conditions
- · Available in rolls
- · Open mesh structure allows flow of water

### Benefits:

- Fast and easy application
- Light weight material compared to alternatives
- Cathodic protection will not negatively be influenced

## **Application examples**

**Pipe coatings:** Protection of coating materials applied on buried or submerged pipes against damages from rocks or geological movements.

**Offshore pipes:** Protection of coating materials during pipe lay, anchors, rock placement, infill and fishing (trawl) activities.

**Splash-zone & underwater installation:** Protection of critical infrastructure like wooden quay walls and piles

General order information	
Product	SFL Rockshield 11 mm is available in rolls with
	following dimensions (W x L):
	Product dimensions:
<b>11 mm</b> [ <sup>7</sup> / <sub>16</sub> "]	1,83 m x 92 m [6 ft x 100 yd]
	Customized pre-cut sizes on request.
Handling	Heavy weight rolls, handle with care.
Storage	Store away from direct sunlight in a cool place.
	Unlimited shelf life.

Product properties of SFL Rockshield 11 mm		
Colour	Black	
Thickness	11 mm [ <sup>7</sup> / <sub>16</sub> "]	
Temperature range	≤ -30 °C to ≥ +100 °C [-22 to +212 °F]	
Weight	1675 g/m² [49.4 oz/yd²]	
Mesh count	28 in 20 cm [8"]	
Aperture size	4 mm x 4 mm [ <sup>5</sup> / <sub>32</sub> " x <sup>5</sup> / <sub>32</sub> "]	
Impact resistance	> 122 : Ib4 [> 4F I]	
(ASTM G14)	≥ 132 in.lbf [≥ 15 J]	
Compressive strength	≥ 620 kPa [90 psi]	
(ASTM D1621)	@ 50 % deformation	
Tensile strength MD	≥ 7,8 kN/m [530 lb/ft]	
(ASTM D4595)	= 7,5 kty iii [550 is/it]	
Elongation at max.	MD: ≥ 139 %	
strength (ASTM D4595)	TD: ≥ 110 %	
Tear strength MD / TD	≥66 N / ≥72 N [14.8 / 16.1 lbf]	
(ASTM D624)		

Application instruction		
Detailed application instructions are available from Seal For Life Industries.		
Additional materials	Installation of SFL Rockshield 11 mm requires the use	
	of complementary SFL Strappingband. Please contact	
	Seal For Life Industries for additional information.	
Equipment, tools and	Installation of SFL Rockshield 11 mm requires the use	
auxiliaries	of SFL Strappingtool, and SFL Strappingband roll	
	carrier. Please contact Seal For Life Industries for additional information.	
Application	SFL Rockshield 11 mm must be wrapped around the	
	entire circumference of the pipe with sufficient	
	circumferential overlap onto itself. Fixation of SFL	
	Rockshield 11 mm to the pipe is accomplished by	
	application of complementary SFL Strappingband.	

Handling and Commissioning	
Exposure to loads	Objects coated with SFL Rockshield 11 mm should not be exposed to excessive loads e.g. from lifting equipment.
Immersion or burying	Immersion or burying is possible immediately after completion of the application. Backfill and compact with clean sand and filling material without sharp stones or hard lumps of soil.

Information	
Documentation	Extensive information is available on our web-site.  Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.



Seal For Life Industries Mexico S de R.L. de C.V. Tijuana, Mexico USA Tel: +1 858 633 9797

USA Tel: +1 858 633 9797 Mx Tel: +52 664 647 4397 mexico@sealforlife.com Seal For Life Industries - Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170

Tel: +31 599 696 170 Fax: +31 599 696 177 info@sealforlife.com Seal For Life Industries BVBA Westerlo, Belgium Tel: +32 14 722 500 Fax: +32 14 722 570

belgium@sealforlife.com

Seal For Life India Private Ltd. Baroda, India Tel: +91 2667 264 721 Fax: +91 2667 264 724 india@sealforlife.com

DISCLAIMER: Seal For Life Industries warrants that the product conforms to its chemical and physical description and is appropriate for the use stated on the technical data sheet when used in compliance with Seal For Life Industries' written instructions. Because many installation factors are beyond the control of Seal For Life Industries, the user shall determine the suitability of the products for the intended uses and assume all risks and liabilities in connection herewith. Seal for Life's liability is stated in its General Terms and Conditions of Sale. Seal For Life Industries makes no other warranty either express or implied. All information contained in this technical data sheet is to be used as a guide and is subject to change without notice. This technical data sheet supersedes all previous data sheets on this product.

V 4 / 20200220 (EN) Page 1 / :